



Bucket

Electrode for high strength joining of low, medium carbon and low alloy steel

Typical Applications:

Buckets, boom, stick, C frame & undercarriage components of earthmoving equipment.

Outstanding Features:

- Low heat input.
- Compatibility with wide range of steels.
- High ductility.
- Excellent crack resistivity.

Recommendation:

For welding of similar and dissimilar combinations of low-medium carbon steels, low alloy steels, manganese steels, etc. as encountered in construction and mining industry.

Procedure:

Clean weld area. Remove all fatigued or cracked metal. Bevel heavy sections 60°-90° vee. Use short arc to deposit stringer beads. Chip slag between passes. Peen deposits in crack-sensitive applications. Prevent localised heat build-up by staggered welding. When welding Manganese steels, do not allow job temperature to exceed 150°C.

Recommended Amperages:

Size (mm)	Amperages
3.15	55-100
4.00	85-140
5.00	135-185

Tensiles Strength: 580 MPa (84,000 psi)